

Lowest Ultrasonic thickness results in mm
 Vessel name: XXXXX XXXXXX

Date: 12 August 2024



GPV Marine
 Services and Surveys

Meters from stern	Transom	1	2	3	4	5	6	7	8	9	10	11	12	13	BOW
Transom		6		6	6	5.8			6					6	
Starboard		6	5.9				6	6	6	6	6	5.8	6	6	
		5.8	5.7	6	6	5.4	5.8	6		6	6	6		5.8	
		5.9	5.9	5.9	5.9	6	6	5.8		5.9	6			5.8	
									5.8	5.9	5.7	5.8			
Underside And centre	Transom 5.5	Transom W/L 5.7	6	9.4	9.8	9.8	10	9.8	10	9.9	10	8.8			
			6	5.7	9.9	9.9	9.9	9.9	10	9.9	10	8.6			
			6		9.9										
	Transom 6	Transom W/L 5.7	10											9.8	
			10												
			10												
Transom 5.6	Transom W/L 5.7	5.8						9.3	10						
		6		9.7	9.5	10	9.6			10	9.9	10			
		6.6	9.5	9.7	10	10	9.9	10	10	10	10	8.6			
Port			5.8	5.9	5.8	5.9	5.6	5.9	5.9		6.1	5.9			
				5.9						5.9		5.7		5.9	
			5.5	5.7		5.6	5.9	6	6		6		5.9	5.7	
					5.6			6		5.7	6		5.9		
													6		
		5.7	5.9	5.9	6	5.9	6	5.9	5.9	6.1	6				
												6.1			

Key					
	Below Waterline	Above Waterline	Uxter Plate	Base Plate	Waterline



Some sample photographs showing the failure of the blacking at the waterline and the wear edge of the base plate.